

Ethyl Acrylate

Description

Ethyl Acrylate is a flammable, colorless, transparent liquid that is easily miscible in organic solvents.

Depending on the monomer selection and chemical reaction conditions, various physical properties can be realized after polymerization.

Properties	Unit	Ethyl Acrylate	Method
Specification			
Purity		≥99.5	
Color		≤10	
Water Content		≤0.05	
Inhibitor		10~20	
Acidity		≤50	
Specific Gravity		0.919~0.923	
Typical Properties			
Boiling Point		99	
Freezing Point		-71	
Refractive Index	nD	1.404	25°C
Heat Capacity	cal/g°C	0.47	20°C
Heat of Polymerization	cal/g	186	
Solubility in Aqueous	wt %	1.5	25°C
aq.in subs	wt %	1.5	25°C
Homopolymer Tg	°C	-24	

Summary

Synonym :

Acrylic acid,ethyl ester

2-Propenoic acid,ethyl ester

/

CAS No : 140-88-5

/

EINECS No : 205-438-8

Chemical Formula

Note

Ethyl acrylate is used in the composition of copolymers with a wide range of industrial applications.

- Resins and emulsion polymers or dispersions for non-woven fabrics, textiles and leather
- Cleaning and floor waxing products
- Synthetic rubbers and latexes, plastics and synthetic resins
- Thickeners or rheology modifiers

Ethyl acrylate is able to addition reaction to the double bond and to polymerize and copolymerize.

Some copolymer reactivity ratios r_1 , r_2 of Ethyl acrylate (M1) with various monomers (M2) was calculated from the Alfred & Price equation.

Styrene : $r_1 = 0.41$ $r_2 = 0.85$

Methyl methacrylate : $r_1 = 0.67$ $r_2 = 1.32$

Vinyl acetate : $r_1 = 18.10$ $r_2 = 0.04$

Precaution

The standard inhibition is 15 ppm Monomethyl Ether of Hydroquinone (MEHQ).

With this inhibitor, the product should be stored at a temperature of no more than 35°C and away from light.

It must also be stored under air atmosphere, as the presence of oxygen is essential to activate the stabilizer. Ethyl acrylate is a highly flammable product, and the usual precautions must be taken in handling it.

For more information, please refer a material safety data sheet.

Package

Ethyl acrylate is delivered :

- 20MT with ISO tank
- 180Kg with steel drum

Issued Date : 2021-12-13

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.