

STYRENE MONOMER

Description

Raw material of Acrylonitrile-Butadiene-Styrene, Expandable Polystyrene, StyreneAcrylonitrile, polystyrene

Application

Basic Petrochemicals

Properties	Method	Unit	STYRENE MONOMER
Aldehyde	ASTM D 2119	wt ppm	MAX 200
Color	SD DC-139	Gardner No	10
Ethylbenzene	Gas Chro	wt %	MAX 500
Peroxide(H ₂ O ₂)	ASTM D-5799	wt ppm	Max 50
Polymer	Gas Chro	wt ppm	MAX 10
Styrene	Gas Chro	wt %	MIN 99.6
TBC	ASTM D-1157	wt ppm	5~20
Total Sulfur	ASTM D-5453	wt ppm	MAX 10

Chemical Formula

C₈H₈

Issued Date : 2022-02-05

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.