

LGflex DINP

Description

DINP is commonly used in a large variety of plastic items.

Application

Compound, Deco Sheet, Flexible Sheet, Hose, Synthetic Leather, Automotive(UBC, BS)

Properties	Method	Unit	LGflex DINP	Condition
Specification				
Color	ASTM D1209		Max 25	
Density	ASTM D1298		0.975 ± 0.003	
Acid Value	JIS K 6751	KOH mg/g	Max 0.05	
Acid value after Heating	JIS K 6751	KOH mg/g	Max 0.1	
Refractive index	JIS K 6751		1.486 ± 0.003	
Ester Contents	LG method	wt %	Min 99.5	
Heating Loss	JIS K 6751	wt %	Max 0.1	
Volume Resistivity	JIS K 6751	x10 ¹¹ Ω.cm	Min 3.0 × 10 ¹¹	
Property				
Molecular Weight			419	
Viscosity		cP	76	20°C
Boiling Point		°C	400	@760mmHg
Freezing Point		°C	-48	
Flash Point		°C	201	

Stability and Reactivity

A. Chemical stability & Possibility of hazardous reactions

- This material is stable under recommended storage and handling conditions.
- Hazardous polymerization will not occur.

B. Conditions to avoid

- Avoid contact with incompatible materials and condition.
- Avoid : Accumulation of electrostatic charges, heating, flames and hot surfaces.

C. Incompatible materials

- Not available

※ This data is based on experimental figures, which are not guaranteed.

Issued Date : 2022-02-10

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.